

Light Reflectance & Total Solar Absorption Values

Colour	Light Reflectance Values 1	Total Solar Absorption 2
--------	----------------------------	--------------------------

Satin Finish

Castle Grey	6.7	93.8
Dark Green	6.7	93.9
Evergreen	9.2	88.4
Graphite	6.7	93.6
Marseille Clay	20.3	69.3
Mint Green	24.3	63.2
Morocco	31.6	70.6
Obsidian	4.6	95.5
Ocean Blue	9.8	91.3
Pearl Grey	26.8	78.6
Russet	8.6	87.4
Smoke Grey	9.1	92.3
Wedgewood	10.3	90.7
Wild Gum	18.0	81.6
Chalk	65.5	42.2

Textured Finish

Ashwood	16.2	84.9
Cedar	5.8	89.3
Charcoal	3.5	96.7
Deep Forest	4.3	95.5
Garnet	5.6	87.0
Greenstone	5.0	92.9
Onyx	9.9	89.3
Pepper	7.9	90.4
Rosso	5.7	88.2
Teak	5.1	92.8
Terracotta	5.8	87.7
Midnight	2.2	95.0
Rainforest	4.4	95.4

Duo-tone Textured Finish

Eclipse	3.5	96.7
Bark	5.1	92.8
Ravine	4.3	95.5

1. ASTM Reference C609-7. Instrument: Macbeth Color-Eye 7000A

2. ASTM Reference C1549 & E903-96. Instrument: Devices & Devices Reflectometer, Model SSR-ER