



Maintenance Schedule for Tray-dec Floors

Where exposed to the elements, galvanised metal decking used for composite flooring systems should be washed regularly to avoid early consumption of the metallic coating.

It is recommended that the exposed area of metal floor is washed using high pressure water blasting every six months. Visual inspection should be carried out every year and if any corrosion is detected this should immediately be repaired.

Where galvanised metal decking is used for composite flooring systems on internal floors, the metal decking

should be inspected annually as part of the routine building maintenance programme.

Where any damage to the metal coating is detected this should be immediately painted to prevent corrosion of the base metal. We recommend using PPG products to protect and repair Tray-dec against atmospheric corrosion.

Please refer to the resources page on our website for the PPG guide as well as further information for prevention and repair of corrosion on Tray-dec sheets.

